




Sintering

Aconia TT-ML SHT-ML Sintering Parameters



Step	Initial Temp	Rate	Final Temp	Time
1	50°C	2.8°C/min	300°C	90min
2	300°C	5°C/min	1520°C	240min
3	1520°C	Holding	1520°C	90min
4	1520°C	-4.5°C/min	800°C	160min
5	800°C		Natural cooling	

Applied to single unit and bridges under 7 units(1-7units)



Wide Shade Selection



Aconia Multilayer Gallery




Aconia 3D MULTI

Seamless Gradient, Seamless Care



- 01 3D - Shade+Strength+Translucency
- 02 CAM - Nesting friendly
- 03 Transition - No layer lines



bSM | Aconia Chengdu Besmile Biotechnology Co., Ltd

Tel: +86-28-85972245
Fax: +86-28-85217510
Email: info@cdbesmile.com
Web: www.bsmdental.com

Add: No.1666, 2nd section of
ChenglongRoad, Chengdu Economic
and Technological Development Zone,
Sichuan, China



bSM | Aconia

Technology Creates the Best Smile

www.bsmdental.com

Aconia 3D Multilayer Technology

- . Excellent esthetic properties with integrated shade and seamless gradient
- . Efficient, economical processing without staining procedure
- . Simplify Zirconia material selection through wide indication application options




What is 3D Multilayer?

- 1 Gradient Chroma:**
Increasing chroma from incisal to cervical
- 2 Gradient translucency:**
Increasing translucency from cervical to incisal
- 3 Gradient flexural strength:**
Increasing flexural strength from incisal to cervical

3D Multilayer	Translucency	Flexural strength
Aconia® <i>TTML</i>	49%	600MPa
	↕	↕
	46%	900MPa
Aconia® <i>SHTML</i>	46%	900MPa
	↕	↕
	43%	1100MPa

Aconia 3D Nesting Technology - Increased body part- 50%



Aconia 3D High Efficiency - Processing Procedure



3D Multilayer	Frequently-used Heights				
	14mm	16mm	18mm	20mm	22mm
20% Incisal part	2.8 mm	3.2 mm	3.6 mm	4 mm	4.4 mm
20% Transition part	2.8 mm	3.2 mm	3.6 mm	4 mm	4.4 mm
50% Body part	7 mm	8 mm	9 mm	10 mm	11 mm
10% Cervical part	1.4 mm	1.6 mm	1.8 mm	2.0mm	2.2mm

Multilayer — TT-ML



Create the best smile with highest esthetics

- . Most natural appearance
- . Perfect option for anterior esthetic restoration
- . Fast and easy processing
- . Creatively maximized efficiency and esthetics

Technical Data	
Flexural Strength (3-point)	600-900 Mpa
Translucency	46-49%
Vickers-hardness HV10	1300±50
Density	>3.00 (g/cm ³)
Sintered Density	>6.02 (g/cm ³)
Chemical Solubility	<50 (μg/cm ³)
Radioactivity	<0.1 (Bq·g ⁻¹)
Fracture toughness	>3 (Mpa·m ^{1/2})
CTE(span25°C-500°C)	(10.5±0.5) *10 ⁻⁶ K ⁻¹

Indication

Veneer	Inlay & Onlay	Reduced crown	Full contour crown	Coping	Full contour anterior bridge (3 units)

Multilayer — SHT-ML



Create the best smile with highest flexibility

- . All-in-one & One-for-all
- . Seamless gradient in translucency, strength and shade
- . Fast and easy processing
- . Revolutionary combination of strength and translucency

Technical Data	
Flexural Strength (3-point)	900-1100 Mpa
Translucency	43-46%
Vickers-hardness HV10	1300±50
Density	>3.00 (g/cm ³)
Sintered Density	>6.02 (g/cm ³)
Chemical Solubility	<50 (μg/cm ³)
Radioactivity	<0.1 (Bq·g ⁻¹)
Fracture toughness	>5 (Mpa·m ^{1/2})
CTE(span25°C-500°C)	(10.5±0.5) *10 ⁻⁶ K ⁻¹

Indication

Inlay & Onlay	Reduced crown	Full contour crown	Coping	Full contour anterior bridge (3 units)	Full contour posterior bridge (3 units)	Full contour bridge (≤7 units)